

EUROSTEP MMA TF

Over concrete or asphalt

Version 1.0 - December 2024

3 layer system applied at 4-6 mm finished off with coloured quartz. System is used in areas which are exposed to mechanical and chemical wear. Designed for environments which need an easy to clean and slip resistant floor.

APPLICATIONS:

- Company kitchens
- Food industry
- Factories
- Carwash

ADVANTAGES:

- Aesthetically pleasing
- Fast installation (can be applied up to - 30 degrees Celsius)
- Adjustable level of antislip
- Easy to clean
- Chemical resistance
- Mechanical strength
- Seamless finish
- UV stable quartz and UV stable MMA
- Durable



CONCRETE INSIDE

Susbstrate	Primer	Consumption	Packaging	Description
1 st layer	Primer Plex 1120 Natural quartz 0,4-0,8	0,4- 0,6 kg/m ² 0,6 - 0,8 kg/m ²	20 kg, 180 kg 25 kg	Standard primer for concrete and damp concrete
2 nd layer	Binder Plex 1510: Plex filler. Quartz, QMI 0,4-0,8	0,9 - 1 kg/m ² 1,8 kg/m ² 4 kg/m ²	20 kg, 180 kg 20 kg 25 kg	Standard binder, used for trowel system or self-leveling
3 rd layer	Topcoat Plex 1690	0,4 - 0,8 kg/m ²	20 kg, 180 kg	Elasticized transparent topcoat

ASFALT INSIDE AND OUTSIDE

Susbstrate	Primer	Consumption	Packaging	Description
1 st layer	Primer Plex 1110 Natural quartz 0,4-0,8	0,4- 0,6 kg/m ² 0,6 - 0,8 kg/m ²	20 kg, 180 kg 25 kg	Elasticized primer used on top of asphalt
2 nd layer	Binder Plex 1520: Plex filler. Quartz QMI 0,4-0,8	0,9 - 1 kg/m ² 1,8 kg/m ² 4 kg/m ²	20 kg, 180 kg 20 kg 25 kg	Elasticized binder used for asphalt
3 rd layer	Topcoat Plex 1690	0,4 - 0,8 kg/m ²	20 kg, 180 kg	Elasticized transparent topcoat

